

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

---

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.

**PCT**WORLD INTELLECTUAL PROPERTY  
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER TI.

WO 9607941A1

(51) International Patent Classification<sup>6</sup>:

G02B 5/30, G02F 1/1335

A1

(11) International Publication Number:

WO 96/07941

(43) International Publication Date:

14 March 1996 (14.03.96)

(21) International Application Number: PCT/US95/11244

(22) International Filing Date: 8 September 1995 (08.09.95)

(30) Priority Data:

08/303,351 8 September 1994 (08.09.94) US

08/387,589 13 February 1995 (13.02.95) US

(60) Parent Application or Grant

(63) Related by Continuation

US

Filed on

08/387,589 (CIP)

13 February 1995 (13.02.95)


(71) Applicant (for all designated States except US): SUMITOMO  
CHEMICAL COMPANY, LIMITED [JP/JP]; 5-33, Kita-  
hama 4-chome, Chuo-ku, Osaka 305 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ANDREATTA, Alejandro  
[VE/US]; 2924 Hermosa Road, Santa Barbara, CA 93105  
(US). DOI, Shuji [JP/JP]; 13-10 202, Amakubo 2-chome,  
Tsukuba, Ibaraki 305 (JP).(74) Agent: BENZ, William, H.; Burns, Doane, Swecker & Mathis,  
P.O. Box 1404, Alexandria, VA 22313-1404 (US).(81) Designated States: CN, JP, KR, SG, US, European patent (AT,  
BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL,  
PT, SE).

Published

With international search report.

~~Before the expiration of the time limit for amending the  
claims and to be republished in the event of the receipt of  
amendments.~~(54) Title: FILM CONTAINING ORIENTED DYE, METHOD OF MANUFACTURING THE SAME, AND POLARIZER AND LIQUID  
CRYSTAL DISPLAY UNIT UTILIZING THE SAME

(57) Abstract

Films containing oriented dye, methods of manufacturing such films, and polarizers and liquid crystal display devices utilizing the films are disclosed. The film contains at least one dichroic dye which is uniaxially oriented. A film has a thickness of not less than 1 nanometer and not greater than 5 micrometer and contains the dichroic dye of not less than 1 percent by weight and not greater than 100 percent by weight. The film has a peak of absorption at 400 nm through 800 nm and a dichroic ratio of not less than 25 at the peak of absorption. The film may include a micro-pattern having a minimum width in a film plane of not less than 1 micrometer and not greater than 200 micrometer. In such a case, the dichroic dye has a dichroic ratio of not less than 10 at the peak of absorption. A method of manufacturing such a film according to the invention includes the step of forming a dye-containing film on a substrate having a fluororesin alignment layer on the surface thereof. The dye-containing film includes at least one dichroic dye or a mixture of at least one dichroic dye and at least one polymer compound. In subsequent steps, the dye-containing film may be stripped off from the substrate and transferred to another substrate.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

FILM CONTAINING ORIENTED DYE, METHOD OF MANUFACTURING THE  
SAME, AND POLARIZER AND LIQUID CRYSTAL DISPLAY UNIT  
UTILIZING THE SAME

5

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention relates to films based upon or containing oriented dye. It also  
10 relates to methods of manufacturing such films and to polarizers and liquid crystal display  
devices utilizing the films. More specifically, the invention pertains to films made of or  
containing highly oriented dichroic dye, methods of manufacturing such films, and high-  
performance polarizers and liquid crystal display devices utilizing the films.

15 Description of Related Art

Polarizers are used as elements of liquid crystal displays (hereinafter referred to as  
LCDs). Polarizers have the property of absorbing some of the light transmitted from the  
LCDs. This becomes a particularly acute problem with full color LCD's since full color  
LCD's contain color filters as well. The polarizer present in the LCD and the color filter  
20 used in the full-color LCDs both absorb light. This reduces the quantity of transmitted light  
to a level that is often quite low. A powerful backlight is thereby required for sufficiently  
bright LCDs. This backlight can undesirably raise the temperature of the liquid crystal cell  
and increase the power consumed. One type of polarizer is manufactured by adsorbing  
iodine onto a uniaxially stretched, oriented alignment film of polyvinyl alcohol (hereinafter  
25 referred to as PVA) or a derivative of PVA.

A second type of polarizer is based on dichroic dyes and is similarly produced by  
adsorbing the dye onto a uniaxially stretched oriented PVA or PVA derivative alignment  
film. (Throughout this specification and claims, the terms "dichroic" and "dichroic dye"  
have their commonly accepted meanings and refer to the property of presenting different  
30 optical properties e.g., color - when viewed from different directions, and thus to in effect  
give a polarized response.)

A third type of polarizer is produced by uniaxially stretching a polyvinyl chloride or  
PVA film and then generating polyene units as chromophores by dehydrohalogenation of the  
polyvinyl chloride or by dehydration of the PVA.

35 The iodine-containing polarizers initially exhibit excellent polarizing power. These  
polarizers, however, have poor resistance to water and heat and are not sufficiently durable  
under conditions of high temperature and high humidity. Protective films or other possible

measures typically do not significantly improve the durability of the iodine-containing polarizers.

The dichroic dye polarizers have greater resistance to water and heat than the iodine-based materials, but have inadequate polarizing properties for most commercial applications.

5 Pigments, which have excellent weather resistance, cannot be substituted since they are not highly oriented in polymer films and thus cannot be used for polarizers.

In addition, many difficulties arise when trying to manufacture fine polarizers such as polarizers having a width of not greater than about 200 micrometers. Cutting a dyed alignment film is the only way presently used to prepare such fine polarizers.

10 Thus, the known methods of orienting dye molecules include the use of an oriented PVA film which aligns the dye molecules as has been described above. It is also known that one can mix a dye with a liquid crystal material and orient the dye as the liquid crystal molecules in the liquid crystal cell are themselves aligned. In the latter method, a liquid crystal material must be sealed between two glass plates or placed within a cell. This method  
15 further requires that an alignment film be formed on the surface of the glass plates. The degree of alignment of the dye depends upon the degree of the alignment of the liquid crystal material, so that in many cases the polarizer does not have a sufficient polarizing power due to low alignment of the liquid crystal material.

Films containing highly oriented dichroic dyes and particularly films which include  
20 micropatterned, highly oriented dichroic dyes and their easy manufacture are thus in high demand.

Although not relating to orienting dye molecules, J.C. Wittmann et al. have found that an oriented polytetrafluoroethylene (hereinafter referred to as PTFE) thin film may be formed by rubbing PTFE while applying heat and pressure. They have reported that  
25 alkanes, liquid crystal molecules, polymers, oligomers, and inorganic salts can be oriented using this oriented PTFE film as an alignment layer (See Nature, Vol. 352, p. 414 (1991) and U.S. Patent No. 5,180,470). While alignment of these organic molecules with this oriented PTFE thin film has been reported in detail, alignment of dye molecules useful for polarizers, or more specifically, alignment of dichroic dye molecules for polarizers, has not  
30 been elucidated.

#### Summary of the Invention

It has now been found that through the use of fluororesin orientation films such as PTFE orientation films, one can achieve highly oriented dichroic dyes. The present  
35 invention concerns these oriented dye-containing films, methods of manufacturing these films; and high performance polarizers and liquid crystal display devices which utilize these films.

Thus, in one aspect, this invention provides a uniaxially oriented film which includes one or more dichroic dyes. This film contains at least 1% by weight dichroic dye up through being completely dichroic dye (100% by weight dye). The remainder is a binder polymer or diluent or the like. The film has a thickness of from 1 nanometer to 5 micrometers, a wavelength of peak absorbance of from 400 to 800 nanometers, and a dichroic absorbance ratio of not less than 25 at the wavelength of peak absorbance.

1 - 5000 nm

In another aspect, this invention provides a body of micro-patterned dye-containing film. This film comprises at least 1% by weight up to 100% by weight of uniaxially oriented dichroic dye. This body of film has a thickness of from 1 nanometer to 5 micrometers and a wavelength of peak absorbance of from 400 to 800 nanometers, and a dichroic absorbance ratio of not less than 10 at the wavelength of peak absorbance. This body has a length and width in the film plane with the width being in the range of from about 1 to about 200 micrometers.

In another aspect, this invention provides a method for manufacturing the uniaxially oriented film just described. This method involves forming a film from a film-forming material which includes at least 1% by weight dichroic dye and has a thickness of from 1 nanometer to 5 micrometers and a wavelength of peak absorbance of from 400 to 800 nanometers. This film-forming takes place on a substrate having a fluoro-resin alignment layer as its surface. This produces a uniaxially oriented film having a dichroic absorbance ratio of not less than 25 at the wavelength of peak absorbance. The film-forming material may in some cases be neat dichroic dye but alternatively may include a film-forming binder polymer mixed with dichroic dye. In more specific aspects, this method may include additional steps of stripping the film from the forming substrate and applying the film to a supporting substrate different from the forming substrate.

In yet an additional aspect, this method may be used to manufacture bodies of micropatterned dye-containing film. In this embodiment, the alignment substrate should have a defined width in the film plain of from about 1 to about 200 micrometers with the fluoro-resin alignment layer being present on the surface in that defined-width region. This will yield bodies of uniaxially oriented film having a defined width of from about 1 to about 200 micrometers and a dichroic absorbance ratio of not less than 10 at the wavelength of peak absorbance. As with the more general method, this method may include the additional steps of stripping the film from the forming substrate and applying the film to a supporting substrate.

In another aspect, this invention provides polarizers. A polarizer results when a transparent support having a planar surface has a uniaxially oriented film as described above attached to its planar surface. Typical transparent supports for such polarizers can be polymer films, glass supports or transparent electrodes.

In an additional aspect, the invention can provide micropolarizers having the same general structure. These micropolarizers include the same type of transparent support carrying a body of the micropatterned dye-containing uniaxially oriented film upon its planar surface.

5 In additional aspects, this invention provides liquid crystal display devices. These devices include a liquid crystal cell containing a pair of separated transparent substrates having electrodes thereon and a nematic liquid crystal layer positioned between the substrates. The nematic liquid crystal layer has a positive dielectric anisotropy and a helical axis aligned vertically to the substrates and oriented substantially horizontally with a twist  
10 angle from 90 to 270 degrees when no voltage is applied. In the display devices of the invention, a uniaxially oriented film or micropatterned dye-containing film or polarizer or micropolarizer as just described is positioned in the path of viewing the LCD. In some embodiments, the uniaxially oriented material is placed outside of and adjacent to the liquid crystal cell. The uniaxially oriented films may be positioned on the transparent substrates of  
15 the liquid crystal cell as well.

#### Brief Description of the Drawings

This invention will be further described with reference being made to the accompanying drawings in which:

20 Fig. 1 is a cross-sectional view illustrating a liquid crystal display device and thin film of this invention;

Fig. 2 is a cross-sectional view illustrating another embodiment of a liquid crystal display device and thin film according to the invention; and

25 Fig. 3 is a graph illustrating the optical absorbance of a film of this invention over the visible spectrum.

Fig. 4 is a graph illustrating the optical absorbance of a film of this invention over the visible spectrum.

Fig. 5 is a graph illustrating the optical absorbance of a film of this invention over the visible spectrum.

30

#### Detailed Description of the Invention

##### The Dye

35 One or more dichroic dyes are present in the films of the present invention. The dye used in the invention may be any dye or pigment meeting the following conditions: It should have an aspect ratio (a length of molecular axis to a length of a molecular perpendicular axis) of not less than 2 and more preferably not less than 3 and it should also have an angle

between its molecular axis and a direction of a transition moment from ground state to excited state that is not greater than 20 degrees. Dyes capable of achieving a high dichroic ratio when oriented with a fluoro-resin alignment layer, as will be described below, are especially preferable. Dyes are preferred which can achieve a dichroic ratio of absorbance (absorbance in the orientation direction to orientation in a direction perpendicular to the orientation direction) at the wavelength of highest adsorption of not less than 5 (preferably not less than 8 and in most cases more preferably not less than 10).


Dichroic dyes used for conventional dipolarizers or guest-host liquid crystal displays are useful and preferred. Types of dichroic dyes used for guest-host liquid crystal displays and useful herein include merocyanines, styryls, azomethines, azos, anthraquinones, quinones, quinophthalones, perylenes, indigos, tetrazines, stilbenes and benzidines. Azo and anthraquinone dichroic dyes having substantial levels of weather resistance are especially preferred. These azo-dyes include diazos and triazos (polyazos).

Azo dyes useful in the invention include materials depicted by general formula I:




In this formula, n is 0 through 3, each Ar represents an aryl group selected from the structures listed in group A, and each Ar' represents an aryl group selected from the structures listed in Group B below:

#### Group A





## Group B



In the above structural formulae,  $X_1$  through  $X_{23}$  independently represent any of  
 5 hydrogen atoms, hydroxyl groups, amino groups, arylamino groups, acylamino groups, alkyl groups containing one through four carbon atoms, alkoxy groups containing one through four carbon atoms, aryl groups containing six through twenty carbon atoms, heterocyclic groups containing four through twenty carbon atoms, carboxylate groups, sulfonate groups, sulfonamide groups, sulfonalkylamide groups, halogens, and nitro  
 10 groups. The number of X groups present on any aromatic ring is equal to the available sites on that ring. For example, in the Group A structure having  $X_1$  as a substituent, there would be five such groups, while in the material shown in Group B with  $X_{13}$ , there would be four such groups, as that is the number of available sites. Two or more different substituent groups may thus be present in one aromatic ring.

15 R represents any of hydrogen atom, alkyl group containing one through four carbon atoms, aryl group containing six through twenty carbon atoms, heterocyclic group containing four through twenty carbon atoms.

Two aromatic rings on either side of the azo radical may carry hydroxyl groups. These hydroxyl groups are located adjacent to the azo structure and can form a complex with  
 20 a transition metal atom selected from the group consisting of copper, nickel, zinc and iron.


Azomethines and stilbenes having an azomethine group and a vinylene group in place of the azo radical of the azo dyes defined by general formula I may also be used as the orientable dyes in the practice of this invention.







Representative useful azo dyes include the azo dyes shown in Table 1-1. These  
 25 materials can exist as transition metal complexes, as free acids and also as salts, for example, sodium salts, lithium, potassium, ammonium, ethanol ammonium, alkyl ammonium salts and the like.







AZOS







Table 1-1







- (1)  $\text{C}_4\text{H}_9\text{OCO}-\text{CH}=\text{CH}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}(\text{C}_2\text{H}_5)_2$
- (2)  $\text{C}_6\text{H}_5-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}(\text{CH}_3)_2$
- 
- (3)  $\text{C}_6\text{H}_5-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_3(\text{OH})(\text{CH}_3)-\text{C}_6\text{H}_4-\text{C}(=\text{O})\text{N}(\text{CH}_3)$
- (4)  $\text{C}_5\text{H}_{11}-\text{C}_6\text{H}_{10}-\text{COO}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_{10}\text{H}_6-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}(\text{CH}_3)_2$
- (5)  $\text{C}_6\text{H}_3(\text{CH}_3)_2-\text{N}=\text{N}-\text{C}_6\text{H}_3(\text{CH}_3)_2-\text{N}=\text{N}-\text{C}_{10}\text{H}_6-\text{NHC}_2\text{H}_5$
- (6)  $\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}(\text{C}_2\text{H}_5)_2$
- (7)  $\text{C}_4\text{H}_5\text{O}_2\text{S}-\text{C}_6\text{H}_3(\text{N}=\text{N})-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}(\text{C}_2\text{H}_5)_2$
- (8)  $\text{C}_4\text{H}_9-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{OC}_3\text{H}_7$
- (9)  $\text{C}_4\text{H}_9-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}(\text{C}_2\text{H}_5)_2$
- (10)  $\text{C}_4\text{H}_9-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_{10}\text{H}_6-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}(\text{C}_2\text{H}_5)_2$
- (11)  $\text{C}_6\text{H}_7\text{O}_2\text{S}-\text{C}_6\text{H}_4-\text{N}=\text{N}-\text{C}_{10}\text{H}_6-\text{N}=\text{N}-\text{C}_6\text{H}_4-\text{N}(\text{C}_2\text{H}_5)_2$




























Other useful azo dyes are those having color index (C.I.) generic names as below:

- |    |                       |
|----|-----------------------|
| 5  | C.I. Direct Orange 39 |
|    | C.I. Direct Yellow 44 |
|    | C.I. Direct Red 28    |
|    | C.I. Direct Blue 151  |
|    | C.I. Direct Red 81    |
| 10 | C.I. Direct Red 23    |

C.I. Direct Red 2  
 C.I. Direct Red 31  
 C.I. Direct Red 37  
 C.I. Direct Red 79  
 5 ~~C.I. Direct Violet 12~~  
 C.I. Direct Violet 9  
 C.I. Direct Yellow 12  
 C.I. Direct Blue 78  
 C.I. Direct Blue 90  
 10 C.I. Direct Blue 202  
 C.I. Direct Yellow 28  
 C.I. Direct Orange 107  
 C.I. Direct Blue 71  
 C.I. Direct Violet 51  
 15 C.I. Direct Orange 26  
 C.I. Direct Red 247  
 C.I. Direct Blue 168  
 C.I. Direct Green 85  
 C.I. Direct Brown 223  
 20 C.I. Direct Brown 106  
 C.I. Direct Yellow 142  
 C.I. Direct Blue 1

25

Useful anthraquinone dyes are illustrated by general formula II:



In this formula R<sub>1</sub>, R<sub>2</sub>, R<sub>3</sub>, R<sub>4</sub>, R<sub>5</sub>, and R<sub>6</sub> independently represent any of hydrogen atoms, hydroxyl groups, amino groups, arylamino groups, acylamino groups, alkyl groups







containing one through four carbon atoms, alkoxy groups containing one through four carbon atoms, aryl groups containing six through twenty carbon atoms, and heterocyclic groups containing four through twenty carbon atoms, provided that all of R<sub>1</sub> through R<sub>6</sub> are not hydrogen atoms. R<sub>2</sub> and R<sub>3</sub> or R<sub>6</sub> and R<sub>7</sub> respectively may be one substituent group which is connected with the anthraquinone group by two linkages.

The anthraquinone dyes useful in the practice of this invention include compounds shown in Tables 2-1, 2-2, 2-3 and 2-4.

Table 2-1

10

Compounds expressed by general formula II, wherein R<sub>1</sub> denotes NH<sub>2</sub>; R<sub>5</sub>, R<sub>6</sub>, R<sub>7</sub> and R<sub>8</sub> denote H; R<sub>2</sub>, R<sub>3</sub> and R<sub>4</sub> denote as shown below.

	R <sub>2</sub>	plus	R <sub>3</sub>	R <sub>4</sub>
52			C <sub>3</sub> H <sub>4</sub> OC <sub>8</sub> H <sub>17</sub>	-NH <sub>2</sub>
53				-NH <sub>2</sub>
54				-NH <sub>2</sub>
55			C <sub>2</sub> H <sub>4</sub> OC <sub>8</sub> H <sub>17</sub>	-NH <sub>2</sub>






Table 2-2

Compounds expressed by general formula II, wherein R<sub>1</sub> denotes NH<sub>2</sub> ; R<sub>4</sub> and R<sub>8</sub> denote OH ; R<sub>2</sub>, R<sub>3</sub>, R<sub>5</sub> and R<sub>7</sub> denote as shown below.





















	R <sub>2</sub>	R <sub>3</sub>	R <sub>5</sub>	R <sub>7</sub>
63		-H	-NH <sub>2</sub>	-H
64		-H	-NH <sub>2</sub>	-H
65		-H	-NH <sub>2</sub>	-H
66		-H	-NH <sub>2</sub>	-H
67	-H		-NH <sub>2</sub>	-H
68	-H		-NH <sub>2</sub>	-H
	R <sub>2</sub>	R <sub>3</sub>	R <sub>5</sub>	R <sub>7</sub>
69	-H		-H	
70	-H		-OH	
71	-H		-OH	
72	-H		-NH <sub>2</sub>	
73	-H			
74	-H			

Table 2-3

Compounds expressed by general formula II, wherein R<sub>1</sub> denotes OH ; R<sub>3</sub> and R<sub>7</sub> denote H ; R<sub>2</sub>, R<sub>4</sub>, R<sub>5</sub>, R<sub>6</sub> and R<sub>8</sub> denote as shown below.

5















	R <sub>2</sub>	R <sub>4</sub>	R <sub>5</sub>	R <sub>6</sub>	R <sub>8</sub>
75		-H	-OH		
76		-OH	-OH		-OH
77		-NHCH <sub>3</sub>	-OH		-NHCH <sub>3</sub>
78	-H		-H	-H	-H

Table 2-4


Compounds expressed by general formula II, wherein R<sub>2</sub>, R<sub>3</sub>, R<sub>4</sub>, R<sub>6</sub>, R<sub>7</sub> and R<sub>8</sub> denote H ; R<sub>1</sub> and R<sub>5</sub> denote as shown below.

5

	R <sub>1</sub>	R <sub>5</sub>
79		
80		
81		

Quinophthalone dyes useful in the practice of this invention are illustrated by general formula (III):


10




In general formula III, A<sub>1</sub>, A<sub>2</sub>, and A<sub>3</sub> independently represent hydrogen atoms, hydroxyl groups, amino groups, arylamino groups, acylamino groups, alkyl groups containing one through four carbon atoms, alkoxy groups containing one through four carbon atoms, aryl groups containing six through twenty carbon atoms, and heterocyclic groups containing four through twenty carbon atoms, provided that all of the A<sub>1</sub> through A<sub>3</sub> groups are not hydrogen atoms at the same time.

15

An example of a quinophthalone dye useful in the practice of this invention is:




- 5       Perylene dyes useful in the practice of the invention are illustrated by general formula IV:



- 10   In general formula IV, A<sub>4</sub> and A<sub>5</sub> independently represent hydrogen atoms, hydroxyl groups, amino groups, arylamino groups, acylamino groups, alkyl groups containing one through four carbon atoms, alkoxy groups containing one through four carbon atoms, aryl groups containing six through twenty carbon atoms, and heterocyclic groups containing four through twenty carbon atoms, provided that both of A<sub>4</sub> and A<sub>5</sub> are not hydrogen atoms at the same time.




An example of a perylene dye preferably used in the practice of this invention is:



(IV')

5

Indigo dyes useful in the practice of the invention are illustrated by general formula V:




(V)

10

In general formula V, Y<sub>1</sub> and Y<sub>2</sub> independently denote NH or S, and A<sub>6</sub> and A<sub>7</sub> independently represent hydrogen atoms, hydroxyl groups, amino groups, arylamino groups, acylamino groups, alkyl groups containing one through four carbon atoms, alkoxy groups containing one through four carbon atoms, aryl groups containing six through  
 15 twenty carbon atoms, and heterocyclic groups containing four through twenty carbon atoms, provided that A<sub>6</sub> and A<sub>7</sub> are not hydrogen atoms at the same time

An example of an indigo dye used in this invention is:



(V')

20

Preferred dyes include azo dyes 1 through 21 in the tables, C.I. Direct Red 28, C.I. Direct Red 81, anthraquinone dyes 52 through 57 and 68 through 77 in the tables, and dyes expressed by the formulae III', IV', and V. Especially preferred dyes are azo dyes 1, 4, 6,  
 25 7, 8, 9, 10, 12, 13, 14, 15, 16, 17, 18, 19, anthraquinone dyes 53, 54, 72, 73, 74, 76, 77, and the dyes expressed by the formulae III', IV' and V'.

### Binders or Film-Forming Polymers

The films of the invention can be constituted entirely of the dichroic dye such as is described above. The film can also be made up of mixtures of dye plus one or more binder materials. These binder materials can be diluents or other inert materials but at present in  
5 amounts greater than a few percent, should be filming.

When a binder material is mixed with the dye, it should be substantially transparent to visible light and capable of being co-deposited with the dye by the method selected. That is, it should vaporize with the dye, be molten with the dye, or be capable of being dissolved with the dye in the solvent of choice. Polymer compounds are typically used as the binder.  
10 Polymer compounds having excellent film-forming ability are preferred as the binder material. Examples of such polymer compounds include poly(vinyl alcohol), poly(ethylene terephthalate), polycarbonate, poly(methyl methacrylate), polyethylene, polypropylene, poly(epsilon-caprolactone), and copolymers and derivatives thereof. Especially preferred are poly(vinyl alcohol), polycarbonate, poly(methyl methacrylate), polyethylene, and  
15 poly(epsilon-caprolactone).

As noted previously, the films of this invention can be made solely of dye, so the binder is an optional component. If binder is present, however, it is generally not present in amounts greater than 99% by weight, not greater than about 95% by weight and more preferably not greater than about 90% by weight, based on the total film composition.  
20

### Properties of the Dye-Containing Film

The thickness of the dye-containing film can be varied as can the dichroic ratio of the dye, the molar absorption coefficient of the dye, and the degree of alignment of the dye in the film. Relatively greater thickness is preferable for preparing a uniform film without pin  
25 holes. Relatively thinner films are preferable for high alignment. Excessively thinner films undesirably increase the single-layer transmittance, thus causing decreased polarization properties in the resulting films.

The thickness of the dye-containing layer typically falls between about 1 nanometer and 5 micrometers, especially from 5 nanometers to 1 micrometer preferable from 10  
30 nanometers to 1 micrometer, and more preferably from 10 nanometers to 0.5 micrometers.

The content of the dye in the dye-containing film can be varied. For best results, the dye content is generally greater than 1 percent by weight. The concentration of dye can range up to 100 percent by weight as some films are formed of neat dye. Preferred concentration ranges are from 5 to 100% by weight and especially 10 through 100% by  
35 weight more preferably from 90 to 100%. The remainder is binder or the like.

The dye-containing film typically has a peak of absorption at 400 to 800 nm. The dichroic ratio at the wavelength of peak absorption should be not less than 25 and preferably

not less than 35. Another characteristic of these films is that their single layer transmittance preferably ranges from 40 to 80 percent.

When the dye-containing film includes a micro-pattern having a minimum width in the film plane of 1 micrometer through 200 micrometer, the preferable dichroic ratio is not less than 10 and more preferably not less than 14. The other conditions are the same as those of the dye-containing film without a micro-pattern.

#### The Alignment Layer and the Preparation Process

The film containing highly oriented dye of this invention is prepared by applying a layer of a dye or a mixture of a dye and a binder over a fluoro-resin alignment layer. The alignment layer has a thickness showing favorable orientation properties. The thickness of the alignment layer is 1 nanometer through 2 micrometer, or more specifically 5 nanometer through 1 micrometer and more preferably 10 nanometer through 0.5 micrometer. The fluoro-resin used in the alignment layer may be any solid fluoro-resin with PTFE, polytrifluoroethylene, and polyvinylidene fluoride (PVDF) being preferred. PTFE is especially preferred.

In some embodiments of this invention the fluoro-resin alignment layer is incorporated into the final devices. In this case the fluoro-resin should be relatively transparent, that is it should have a sufficiently small absorbance in at least a portion of the visible spectrum to allow useful levels of light to pass. If the film is stripped from the alignment layer, this transparency is obviously moot.

The fluoro-resin alignment layer is prepared by any known method. For example, the method disclosed in U.S. Patent No. 5,180,470 may be used to provide highly oriented films. That method includes the step of rubbing a fluoro-resin block against a heated substrate while applying pressure. The substrate is preferably cleansed before preparing the alignment layer on it. The method of cleansing can be varied with the material of the substrate. For example glass or heat resistant plastic substrates can be exposed to a plasma generated in a glow discharge apparatus or the like. Alternatively or in addition, the substrate can be washed with a fluid such as a liquid. This liquid can be aqueous, nonaqueous or mixed aqueous-nonaqueous. Nonaqueous liquid can include organic liquids such as lower halohydrocarbons, lower alcohols, ketones, or the like of nonorganic liquids such as halocarbons. These wash liquids can contain acids, bases, detergents, surface active agents and like wash aids. To obtain higher dichroic ratios, glass substrates are preferably washed with a solution containing water and alkali, particularly a mixed aqueous-nonaqueous solution of alkali and especially an alkali metal hydroxide (most preferably potassium hydroxide) in a mixed water-lower alcohol solvent (most preferably a mixed water-ethanol solvent.) The heating temperature is varied with the type of resin, but is

generally in the range of from about 100°C to about 350°C or the decomposition temperature of the resin, if that is lower. Preferred temperatures range between 130°C and 330°C. More preferred temperatures range between 250°C and 330°C. The pressure and rubbing speed may be determined by experimentation, but commonly range between 0.5 and 5 MPA and from 0.01 cm/second to 10 cm/second. These conditions assure uniformity and excellent orientation of the alignment layer.

#### Preparation Methods

The dye-containing film may, in one embodiment, be prepared by vacuum-depositing a suitable orientable dye onto the fluororesin alignment layer. Alternatively, one can apply a molten dye or a dye solution onto the fluororesin alignment layer. In any of these approaches, the dye-containing film may be neat dye or it may be dye plus binder or polymer material.

In the vacuum deposition process, the dye (and possible binder) is heated in a vacuum at a temperature below the dye and/or binder's decomposition point. The dye sublimates and is accumulated on the alignment layer. The dye and binder employed in this case should be selected to not decompose but be capable of being deposited by vacuum and the application of heat such as temperatures in the range of 125° C to as much as 300° C.

In the process where the dye is deposited as a molten phase, the dye or dye plus binder is melted at a temperature again that should be below the decomposition point for the dye or the binder and applied onto the alignment layer. The dye used in this process should be capable of melting by application of heat and stable in liquid state, again, typically in the 125-300° range.

In the process of application where a solution of dye is employed, the dye plus solvent is applied onto the alignment layer and the solvent subsequently removed by vaporization. The dye used in this process should have a solubility in the solvent of not less than about 0.1 percent by weight. This dye should be stable in solution and capable in solution and capable of forming a thin, uniform film.

The solvent employed is typically an organic solvent but in the case of neat dyes in some cases may be an aqueous solvent. Representative organic solvents for use with dyes and dye-binder mixtures should be selected from hydrocarbons, halohydrocarbons, oxyhydrocarbons and the like known in the art as solvents for organic materials and polymers.

Among these three methods, the vacuum depositing method is preferred at this time. At this time, it gives the highest degree of control of the film thickness and the degree of alignment.

In a preferred embodiment, a film having other functions may be laid down on the polarizer film containing oriented dye. This additional film may be a protective overlayer or hard coat such as one made of epoxy resin or a photo-setting resin.

#### 5 The Substrate

The alignment layer is commonly supported by a substrate. In cases where the aligned dye-containing film is to be used directly, that is, without being removed from the alignment layer and its substrate, the substrate should be transparent to visible light as is the alignment layer and sufficiently smooth on its surface to give a good support to the alignment layer. (As used herein the term "transparent" defines the property of a material of passing a substantial proportion, e.g. at least about 33% of a desired underlength of light impinged upon it.)

Preferred examples of the substrate include glass, poly(ethylene terephthalate), and polycarbonate.

15 In those cases where the dye-containing film formed on the alignment layer on the forming substrate is stripped off or transferred to another substrate, the forming substrate need not be transparent and metal plates, metal rolls, and metal-coated plates or rolls may be used as the substrate. Metal materials used as a substrate may be stainless steel or nickel plated metals.

20 The alignment layer and the dye-containing film can be formed directly on such substrates when they have sufficient heat resistance. Glass is an example of a substrate having sufficient heat resistance for direct formation of the alignment layer and dye-containing film. In those situations where the substrate does not have sufficient heat resistance to permit the alignment film to be formed directly upon it, the alignment film and dye-containing film are first formed on a substrate having sufficient heat resistance and then transferred to the other substrate, the subsequent substrate typically being transparent and the like.

#### Applications of the Dye-Containing Films

30 The dye-containing films of this invention are employed as polarizers. In such an application, a dye-containing film is typically formed upon a preformed fluororesin alignment film having the required area for the polarizer.

In another preferred application, the film containing the oriented dye can be configured to include a micro-pattern having a width in the film plane of from 1 to 200 micrometers. Such a film is prepared by first patterning an alignment layer in advance or by patterning an alignment layer after it is produced using a mask. This latter method which

uses a mask is easily implemented by conventional lithography processes and is thus preferred. This method of patterning is described briefly.

To form a micropolarizer, a fluoro-resin alignment layer is first formed over a substrate using the methods described above. A photoresist is then applied on the alignment layer by spin coating or other appropriate process. The photoresist may be either a negative type or a positive type corresponding to a mask of the desired pattern. The photoresist is typically applied as a solution. After heat treatment (pre-baking) to remove the solution's solvent, the alignment film with its mask is exposed to light. The light source used is selected to have a wavelength and an intensity suitable for reacting with the photoresist. The pattern of the photoresist is developed using conventional photoresist mask technology. A large enough surface of the alignment area should be free of the photoresist to permit orienting the dye. A dye-containing film is subsequently formed on the patterned alignment layer using any of the methods described above. The dye is oriented on those regions of the alignment layer which have been exposed. The dye is not oriented on those areas of the alignment layer which are covered with the photoresist. In a subsequent step, that portion of the dye deposited upon the photoresist may be removed together with the photoresist.

The dye-containing film which results will carry a micro-pattern and forms a fine polarizer having a high degree of resolution and can be used as a color filter having polarizing properties.

The dye-containing film in some cases is employed together with the substrate. In other cases, when the dye-containing film has sufficient strength, it may be stripped off of the substrate. In this case, the dye-containing film formed on the substrate may be mechanically stripped from the substrate or may be released by soaking the film in an appropriate release agent.

The dye-containing film or the micro-patterned dye-containing film prepared as just described may be transferred to another substrate for use. When this is done, the dye-containing film should be affixed to the new substrate such as by being strongly pressed against the substrate which has better adhesive properties for the dye film, by the use of heat, or by the use of an adhesive.

#### Liquid Crystal Display Devices

A primary application of the films of this invention is as part of liquid crystal display devices. The liquid crystal display devices of the present invention are not limited except that the liquid crystal display devices should include a polarizer that itself includes a dye-containing film of this invention or a micropolarizer which contains a micro-patterned dye-containing film of this invention.

Liquid crystal display devices of this invention are prepared by placing an appropriately sized polarizer, including the dye-containing films of this invention outside of a liquid crystal cell or by similarly placing a micropolarizer which includes the micro-patterned dye-containing film of the invention.

5 In one particular application, the micro-patterned dye-containing film of the invention

has a micro-pattern corresponding to pixels, and may be positioned outside the liquid crystal cell or between the liquid crystal layer and one of the substrates of the liquid crystal cell. The micro-patterned dye-containing film of the invention may also be formed on the transparent electrode of the liquid crystal cell and thus employed in the liquid crystal device.

10 Figs. 1 and 2 are not-to-scale cross-sectional views illustrating examples of the liquid crystal display device employing the dye-containing films of the present invention. In Figs. 1 and 2, liquid crystal display devices 10 and 20 are shown to include a polarizer according to the invention, 1, a micropolarizer according to this invention, 1'; a glass substrate, 2; a transparent electrode, 3; an insulating alignment layer, 4; a liquid crystal layer, 5; and a  
15 spacer 6.

In Fig. 2, although the micropolarizer 1' is formed between the transparent electrode 3 and the insulating alignment layer 4, micropolarizer 1' may also be formed below the transparent electrode 3 and the insulating alignment layer 4. The transparent electrode 3 is formed on one face of glass substrate 2 close to the liquid crystal layer 5 and typically  
20 includes a transparent conductive material such as ITO (indium tin oxide),  $\text{In}_2\text{O}_3$ , or  $\text{SnO}_2$  or the like. The insulating alignment layer 4 is present between the transparent electrode 3 and the liquid crystal layer 5. The insulating alignment layer 4 may include only an alignment layer having sufficient insulating properties or may include a separate alignment and a separate insulating layer formed below the alignment layer. The alignment layer 4  
25 used here may be any known organic or inorganic, low molecular weight (oligomeric) or high molecular weight polymeric film compounds. Examples of the high molecular weight film compounds include polyimide, polyamide, poly(amide-imide), poly(vinyl alcohol), polystyrene, polyester, poly(ester-imide), and a variety of photoresists.

The alignment of liquid crystal molecules in layer 5 is further improved by rubbing  
30 the polymer alignment layer 4 with gauze or flocked polyacetate fabric.

When a separate insulating layer is present it may be selected from dielectric materials such as titanium oxides, aluminum oxides, zirconium oxides, silicon oxides, and silicon nitrides and the like. The alignment layer and the insulating layer are formed according to any appropriate method. For polymer alignment layers, a polymer compound or a precursor  
35 thereof is dissolved in a solvent and applied by screen printing, spin applying, or dip coating. For inorganic alignment layers, an inorganic compound is applied by dip coating, sputter, deposition, or rhombic deposition.

The thickness of the insulating alignment layer 4 is not limited. Typical thicknesses are from 1 nanometer to 2 micrometers, and more preferably from 1 to 100 nanometers.

In the liquid crystal display devices of the invention, a pair of glass substrates 2 each having a transparent electrode 3 and a insulating alignment layer 4 are spaced apart from each other with spacers 6. The spacers 6 may be insulating beads, fibers, or films. Typically, these are composed of silica, alumina, or a polymer and have a predetermined diameter or thickness to provide the desired spacing. After the pair of glass substrates 2 with the spacers 6 therein are sealed, for example, with an epoxy adhesive, a liquid crystal material is poured into the space between the substrates 2.

One or two polarizers 1 consisting of a dye-containing film of the invention are positioned outside the glass substrates 2. In the example shown in Fig. 1, two polarizers 1 are positioned outside the glass substrates 2. In the example of Fig. 2, a micro-polarizer 1' made up of a micro-patterned dye-containing film of the invention is positioned between the transparent electrode 3 and the insulating alignment layer 4 of the liquid crystal cell.

The transparent electrodes are connected to an external driving circuit 12 via lead wires 14 and 16.

As described above, the dye-containing film of the invention is easily manufactured to have an appropriate thickness, a high dichroic ratio, and an excellent single layer transmittance suitable for use as a polarizer. The polarizer or micro-polarizer and the liquid crystal display devices which utilize them have desirable contrast properties.

## EXAMPLES

This invention will be further described by the following examples. Since there may be many modifications, alterations, and changes to the specific embodiments set forth in these examples without departing from the spirit and scope of the essential characteristics of this invention, the examples are only illustrative and not to be construed as limiting the scope of this invention.

The dichroic ratio mentioned in these examples is expressed as  $A1/A2$ , where A1 represents an absorbance of a polarized light in a direction parallel to an alignment of a dye-containing film and A2 represents an absorbance of polarized light in a direction perpendicular to the alignment of the dye-containing film. The absorbances A1 and A2 are measured at the wavelength of peak absorption, and determined respectively by subtracting a substrate-attributed absorbance from the measured value.



## Example 1

## (Formation of Alignment Layer)

A PTFE alignment layer was prepared according to the method disclosed in U.S. Patent No. 5,180,470. A PTFE bar having a diameter of 1.0 cm was pressed against a glass substrate (2.5 cm x 8.0 cm) heated at approximately 300°C, under application of a pressure of approximately 0.7 MPa. A PTFE alignment layer having a width of 1.0 cm and a length of 7.0 cm was prepared by moving the substrate at a speed of 0.1 cm/second.

## (Formation of Dye-containing Film)

10 An azo dye G205 (Nihon Kanko Shikiso Co., Ltd.), was vapor deposited on the PTFE alignment layer thus prepared. The vacuum was less than  $10^{-5}$  torr and the speed of deposition was 1 nm/second. The thickness of the dye-containing film thus obtained was 53 nm.

## 15 (Evaluation of Dichroic Ratio)

The absorbance of the G205 film obtained was measured in the range of 300 through 700 nm of polarized light. The dichroic ratio at the absorption peak was 86 as shown in Fig. 3.

20 Dye-containing films prepared as above are placed at an orientation of 90 degree-twisting on both sides of a twist nematic (TN) liquid crystal cell. The TN liquid crystal cell has a variation in non-color and red, thus showing a favorable contrast when the cell is driven.

## Example 2

## 25 (Formation of Dye-containing Film)

An azo dye G232 (Nihon Kanko Shikiso Co., Ltd.) was deposited on a PTFE alignment layer prepared in the same manner as described in Example 1. The vacuum was less than  $10^{-5}$  torr and the speed of deposition was 1 nm/second. The thickness of the dye-containing film thus obtained was 164 nm.

30

## (Evaluation of Dichroic Ratio)

The absorbance of the G232 film obtained was measured in the range of 300 through 700 nm of polarized light. The dichroic ratio at the absorption peak was 40 as shown in Fig. 4.

35

Dye-containing films prepared as above are placed at an orientation of 90 degree-twisting on both sides of a TN liquid crystal cell. The TN liquid crystal cell has a variation in non-color and yellow, thus showing a favorable contrast when the cell is driven.

### 5 Example 3

#### (Formation of Micro-patterned Dye-containing Film)

A positive photoresist MICROPOSIT Photoresist (Shiplay Far East Ltd.) was spin-coated at 4000 rpm on a PTFE alignment layer prepared in the same manner as Example 1, and heat-treated (pre-baked) at 90°C for thirty minutes. The thickness of the photoresist was  
10 1.2 micrometer. The alignment layer with a mask was then exposed to light emitted from an ultraviolet light source (436 nm and 405 nm, 50 mJ/cm<sup>2</sup>). The alignment layer was then washed with a developing agent MICROPOSIT Developer (Shiplay Far East Ltd.) for removal of the photoresist on the exposed portion. The minimum width of the photoresist and the minimum width of the exposed alignment layer were 3 micrometer and 5  
15 micrometer, respectively.

An azo dye G205 (Nihon Kanko Shikiso Co., Ltd.) was deposited on the micro-patterned alignment layer thus prepared. The degree of vacuum was less than 10<sup>-5</sup> torr and the speed of deposition was 1 nm/second. The thickness of the dye-containing film thus  
20 obtained was 45 nm.

#### (Evaluation of Dichroic Ratio)

The absorbance of the G205 film obtained was measured in the range of 300 through 700 nm of polarized light. The dichroic ratio at the absorption peak was 14.

Three sets of measurements were taken. One set of measurements was made on the  
25 aligned dye layer present in the micropattern between the photoresist areas. These measurements are shown in Fig. 5 as line 17 (absorbance of polarized light parallel to the oriented PTFE chains) and line 18 (absorbance of polarized light perpendicular to the oriented PTFE chains). The dichroic ratio was calculated from these data.

The second set of measurements was made on the micropatterned photoresist itself.  
30 These measurements are shown in Fig. 5 as line 19 (absorbance of polarized light perpendicular to the oriented PTFE chains) and line 20 (absorbance of polarized light parallel to the oriented PTFE chains).

The third set of measurements was made on the oriented PTFE layer itself. These measurements are shown in Fig. 5 as line 21 (absorbance of polarized light perpendicular to the oriented PTFE chains) and line 22 (absorbance of polarized light parallel to the oriented  
35 PTFE chains). The data from the second and third sets of measurements show that the high

dichroic ratio is not the result of the substrate alone nor of the photoresist alone but rather is the result of the dye being present on the micropatterned aligned PTFE substrate.

The micro-patterned dye-containing film prepared as above is placed between an electrode and an insulating alignment layer of a TN liquid crystal cell while the dye-  
5 containing film of Example 1 is placed at an orientation of 90 degree-twisting on one side of the TN liquid crystal cell. The TN liquid crystal cell has a variation in non-color and red, thus showing a favorable contrast when the cell is driven.

The liquid crystal display device shown in Fig. 1 or Fig. 2 is prepared by combining a polarizer consisting of a dye-containing film or a micro-polarizer consisting of a micro-  
10 patterned dye-containing film with a liquid crystal cell containing a pair of transparent substrates having electrodes thereon and a nematic liquid crystal layer positioned between the substrates. The crystal layer contains a nematic liquid crystal having a positive dielectric anisotropy and its helical axis aligned vertically to the substrate. The crystal layer is oriented substantially horizontally in the twist angle range of not less than 90 degrees and not greater  
15 than 270 degrees when no voltage is applied. The liquid crystal display device thus prepared has excellent display properties including a favorable contrast.

As described above, the dye-containing film of the invention including a fluororesin as an alignment film is easily manufactured to have an appropriate thickness, a high dichroic ratio, and an excellent single layer transmittance suitable for a polarizer. The polarizer or  
20 micro-polarizer and the liquid crystal display device utilizing the dye-containing film have preferable contrast properties.

## WHAT IS CLAIMED IS:

1. A uniaxially oriented film comprising at least 1% by weight dichroic dye and  
5 ~~having a thickness of from 1 nanometer to 5 micrometers, a wavelength of peak absorbance~~  
of from 400 to 800 nanometers, and a dichroic ratio of not less than 25 at the wavelength of  
peak absorbance.
2. A uniaxially oriented film comprising dichroic dye from 10 to 100% by weight  
10 and having a thickness of from 10 nanometer to 1 micrometer. A wavelength of peak  
absorbance of from 400 to 800nm, a dichroic ratio of not less than 35 at the wavelength of  
peak absorbance and a transmittance of from 40 to 80% at the wavelength of peak  
absorbance.
- 15 3. A uniaxially oriented film comprising dichroic dye from 90 to 100% by weight  
and having a thickness of from 10 nanometers to 0.5 micrometers, and a dichroic ratio of not  
less than 35.
- 20 4. The uniaxially oriented film of Claim 1 comprising an admixture of binder  
polymer and at least 10% by weight dichroic dye, having a thickness of from 10 nanometers  
to 5 micrometers, a wavelength of peak absorbance of from 400 to 800nm, and a dichroic  
ratio of not less than 25 at the wavelength of peak absorbance.
- 25 5. The uniaxially oriented film of Claim 1 wherein the dye has an aspect ratio of not  
less than 2.
6. A body of micro-patterned dye-containing film comprising at least 1% by weight  
uniaxially oriented dichroic dye and having a thickness of from 1 nanometer to 5  
micrometers, a wavelength of peak absorbance of from 400 to 800 nanometers, and a  
30 dichroic ratio of not less than 10 at the wavelength of peak absorbance, said micropattern  
having a length and width in the film plane with the width being from 1 to 200 micrometers.
7. The body of micro-patterned dye-containing film of Claim 6 consisting essentially  
of dichroic dye from 90 to 100% by weight.
- 35 8. The body of micro-patterned dye-containing film of Claim 6 comprising an  
admixture of binder polymer and at least 1% by weight dichroic dye.

9. The body of micro-patterned dye-containing film of Claim 6 wherein the dye has an aspect ratio of not less than 2.

5           10. A uniaxially oriented film of a film-forming material comprising at least 1% by weight dichroic dye, said dye having a wavelength of peak absorbance of from 400 to 800 nanometers, the film having a thickness of from 1 nanometer to 5 micrometers, having a dichroic ratio of not less than 25 at the wavelength of peak absorbance and having been formed by deposit of the film-forming material upon a fluororesin alignment layer.

10

11. The film of Claim 10 wherein the fluororesin is PTFE.

12. A body of micro-patterned dye-containing film of a film-forming material comprising at least 1% by weight uniaxially oriented dichroic dye, said dye having a wavelength of peak absorbance of from 400 to 800 nanometers, the film having a thickness of from 1 nanometer to 5 micrometers, having a dichroic ratio of not less than 10 at the wavelength of peak absorbance, a micropattern width of from 1 to 200 micrometers and having been formed by deposit of the film-forming material upon a micropatterned fluororesin alignment layer.

15  
20

13. A uniaxially oriented film comprising at least 1% by weight dichroic dye and having a thickness of from 10 nanometer to 1 micrometers, a wavelength of peak absorbance of from 400 to 800 nanometers, a dichroic ratio of not less than 35 at the wavelength of peak absorbance, and a transmittance of from 40 to 80% at the wavelength of peak absorbance on a fluororesin alignment layer.

25

14. A body of micro-patterned dye-containing film comprising at least 1% by weight uniaxially oriented dichroic dye and having a thickness of from 1 nanometer to 5 micrometers, a wavelength of peak absorbance of from 400 to 800 nanometers, and a dichroic ratio of not less than 10 at the wavelength of peak absorbance, said micropattern having a length and width in the film plane with the width being from 1 to 200 micrometers on a fluororesin alignment layer.

30

15. A method for manufacturing a uniaxially oriented film, the method comprising the step of

35

a) forming a film from a film-forming material comprising at least 1% by weight dichroic dye and having a thickness of from 1 nanometer to 5 micrometers, a wavelength of

peak absorbance of from 400 to 800 nanometers on a fluoro-resin alignment layer, thereby yielding a uniaxially oriented film having a dichroic ratio of not less than 25 at the wavelength of peak absorbance.

5           16. The method of claim 15 wherein the film-forming material additionally comprises a film-forming polymer.

---

10           17. The method of claim 15 comprising the additional steps of  
b) stripping the film from the alignment layer and  
c) applying the film to a supporting substrate.

15           18. A method for manufacturing a body of micro-patterned dye-containing film comprising  
a) forming a film of a film-forming material comprising at least 1% by weight  
uniaxially oriented dichroic dye and having a thickness of from 1 nanometer to 5  
micrometers, a wavelength of peak absorbance of from 400 to 800 nanometers on a  
fluoro-resin alignment layer having a defined width in the film plane of from 1 to 200  
micrometers thereby yielding a body of uniaxially oriented film having a defined width of  
from 1 to 200 micrometers and a dichroic ratio of not less than 10 at the wavelength of peak  
20 absorbance.

25           19. The method of claim 18 comprising the additional steps of  
b) stripping the film from the alignment layer and  
c) applying the film to a supporting substrate.

20           20. A polarizer comprising a transparent support having a planar surface carrying a uniaxially oriented film of claim 1.

30           21. The polarizer of claim 20 wherein the support is a polymer film.

22. The polarizer of claim 20 wherein the support is a glass plate.

23. The polarizer of claim 20 wherein the support is a transparent electrode.

35           24. A polarizer comprising a transparent support having a planar surface carrying a uniaxially oriented film of claim 10.

25. A micropolarizer comprising a transparent support having a planar surface carrying a body of micro-patterned dye-containing uniaxially oriented film of claim 6.

26. The micropolarizer of claim 25 wherein the support is a polymer film.

5

27. The micropolarizer of claim 25 wherein the support is a glass plate.

28. The micropolarizer of claim 25 wherein the support is a transparent electrode.

10 29. A micropolarizer comprising a transparent support having a planar surface carrying a body of micro-patterned dye-containing uniaxially oriented film of claim 12.

30. A liquid crystal display device comprising  
a liquid crystal cell containing a pair of separated transparent substrates having  
15 electrodes thereon and a nematic liquid crystal layer positioned between the substrates, the  
nematic liquid crystal layer having a positive dielectric anisotropy and a helical axis aligned  
vertically to the substrates and oriented substantially horizontally with a twist angle of from  
90 to 270 degrees when no voltage is applied and  
a polarizer of claim 20 positioned adjacent to a transparent electrode of the liquid  
20 crystal cell.

31. The display device of claim 30 wherein the polarizer is outside of the cell.

32. The display device of claim 30 wherein the polarizer is between the liquid crystal  
25 layer and a transparent electrode.

33. A liquid crystal display device comprising  
a liquid crystal cell containing a pair of separated transparent substrates having  
electrodes thereon and a nematic liquid crystal layer positioned between the substrates, the  
30 nematic liquid crystal layer having a positive dielectric anisotropy and a helical axis aligned  
vertically to the substrates and oriented substantially horizontally with a twist angle of from  
90 to 270 degrees when no voltage is applied and  
a polarizer of claim 24 positioned adjacent to a transparent electrode of the liquid  
crystal cell.

35

34. A liquid crystal display device comprising  
a liquid crystal cell containing a pair of separated transparent substrates having electrodes thereon and a nematic liquid crystal layer positioned between the substrates, the nematic liquid crystal layer having a positive dielectric anisotropy and a helical axis aligned  
5 vertically to the substrates and oriented substantially horizontally with a twist angle of from 90 to 270 degrees when no voltage is applied and  
a micropolarizer of claim 25 positioned adjacent to a transparent electrode of the liquid crystal cell.
- 10 35. The display device of claim 33 wherein the polarizer is outside of the cell.
36. The display device of claim 34 wherein the micropolarizer is between the liquid crystal layer and a transparent electrode.
- 15 37. A liquid crystal display device comprising  
a liquid crystal cell containing a pair of separated transparent substrates having electrodes thereon and a nematic liquid crystal layer positioned between the substrates, the nematic liquid crystal layer having a positive dielectric anisotropy and a helical axis aligned  
vertically to the substrates and oriented substantially horizontally with a twist angle of from  
20 90 to 270 degrees when no voltage is applied and  
a micropolarizer of claim 29 positioned adjacent to a transparent electrode of the liquid crystal cell.






FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 95/11244

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 G02B5/30 G02F1/1335

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 G02B G02F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,5 340 504 (CLAUSSEN UWE) 23 August 1994	1,2
A	see the whole document	3,4,6, 10, 12-16, 18,20, 24,25, 30,33, 34,37
A	EP,A,0 518 425 (DSM NV) 16 December 1992	1-4,6, 10, 12-16, 18,20, 24,25, 30,33, 34,37
	see the whole document	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*Z\* document member of the same patent family

Date of the actual completion of the international search

11 January 1996

Date of mailing of the international search report

19. 01. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

Ward, S

# INTERNATIONAL SEARCH REPORT

Int. onal Application No  
PCT/US 95/11244

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US,A,4 416 946 (BOLT LAWRENCE) 22 November 1983</p> <p>see the whole document ---</p>	<p>1-3,6, 10, 12-15, 18,20, 24,25, 30,33, 34,37</p>
A	<p>US,A,4 396 646 (SCHULER NORMAN W ET AL) 2 August 1983</p> <p>see the whole document ---</p>	<p>1-3,6, 10, 12-15, 18,20, 24,25, 30,33, 34,37</p>
A	<p>US,A,5 327 285 (FARIS SADEG M) 5 July 1994</p> <p>see the whole document ---</p>	<p>1-3,6, 10, 12-15, 18,20, 24,25, 30,33, 34,37</p>
A	<p>NATURE, vol. 352, 1 August 1991 pages 414-417, WITTMAN ET AL 'Highly Oriented Thin Films of Poly(tetrafluoroethylene) as a substrate for oriented growth of materials' cited in the application see the whole document ---</p>	<p>1-3,6, 10, 12-15, 18,20, 24,25, 30,33, 34,37</p>
A	<p>US,A,5 343 318 (BASTURK NACI) 30 August 1994</p> <p>see the whole document ---</p>	<p>1-3,6, 10, 12-15, 18,20, 24,25, 30,33, 34,37</p>
A	<p>US,A,5 180 470 (SMITH PAUL ET AL) 19 January 1993 cited in the application</p> <p>see the whole document -----</p>	<p>1-3,6, 10, 12-15, 18,20, 24,25, 30,33, 34,37</p>

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Application No

PCT/US 95/11244

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-5340504	23-08-94	DE-A- 4103346 EP-A- 0498217 JP-A- 5098171	06-08-92 12-08-92 20-04-93
EP-A-0518425	16-12-92	NL-A- 9101008 JP-A- 5154902 US-A- 5312568 US-A- 5258208	04-01-93 22-06-93 17-05-94 02-11-93
US-A-4416946	22-11-83	NONE	
US-A-4396646	02-08-83	US-A- 4466704	21-08-84
US-A-5327285	05-07-94	NONE	
US-A-5343318	30-08-94	FR-A- 2667166 WO-A- 9205465 DE-D- 69106639 EP-A- 0476527 JP-T- 5502740	27-03-92 02-04-92 23-02-95 25-03-92 13-05-93
US-A-5180470	19-01-93	NONE	